

Unconventional electronic Raman spectra of borocarbide superconductors

In-Sang Yang^{1,2}, M.V. Klein², T.P. Devereaux³, I.R. Fisher⁴, and P.C. Canfield⁴

¹Department of Physics, Ewha Womans University, Seoul 120-750, Korea

²Science and Technology Center for Superconductivity and Department of Physics, University of Illinois, Urbana, IL 61801.

³Department of Physics, University of Waterloo, Waterloo, Canada, N2L 3G1

⁴Ames Laboratory, Department of Physics and Astronomy, Iowa State University, Ames, IA 50011.

Borocarbide superconductors, which are thought to be conventional BCS-type superconductors, are not so conventional in several electronic Raman properties. Anisotropic gap-like features and finite scattering strength below the gap were observed for the $R\text{Ni}_2\text{B}_2\text{C}$ ($R = \text{Lu}, \text{Y}$) systems in our previous study.[1] The effects of Co-doping on the 2Δ gap-like features and the finite scattering strength below and above the gap are studied in $R = \text{Lu}$ ($\text{B} = \text{B}^{11}$) system. In superconducting states, Co-doping strongly suppresses the 2Δ peak in both B_{2g} and B_{1g} symmetries. Raman cross-section calculation which includes inelastic scattering shows a relatively good fit to the features above the 2Δ peak, while it does not fully account for the features below the peak.

Some superconductors that are thought to be of the conventional BCS-type have unusual properties. Especially, the borocarbides with the generic formula $R\text{Ni}_2\text{B}_2\text{C}$ ($R = \text{Y}$, rare earths) have shown rich physics.[2] In this article, we further address the peculiar behavior of the 2Δ peak and the sub-gap features, reported in our earlier electronic Raman measurements[1], in the $\text{Lu}(\text{Ni}_{1-x}\text{Co}_x)_2\text{B}_2\text{C}$ ($x = 0.0, 0.015, 0.03$).

The samples measured were single crystals grown by the flux-growth method[3] and characterized by temperature-dependence of resistivity and magnetization.[4] Raman spectra were obtained using a custom-made subtractive triple-grating spectrometer designed for very small Raman shifts and ultra low intensities. 3 mW of 6471 Å Kr-ion laser light was focused onto a spot of $100 \times 100 \mu\text{m}^2$, in a pseudo-backscattering geometry. The temperature of the spot on the sample surface was estimated to be ~ 7 K for the superconducting spectra. The spectra were corrected for the response of the spectrometer and the Bose factor. Thus they are proportional to the imaginary part of the Raman susceptibility.

The 7 K Raman spectra in both geometries show 2Δ -like peak features. The intensity of the 2Δ -like peak is stronger and sharper in B_{2g} than in B_{1g} . They are strongly suppressed as pure $\text{LuNi}_2\text{B}_2\text{C}$ is doped by Co on the Ni sites. The

Co impurities are believed to be nonmagnetic.[4]

The $T \rightarrow 0$ peak positions of the 2Δ -like feature, which were found to show BCS-type temperature dependence of the superconducting gap $\Delta(T)$, are 45 cm^{-1} (B_{2g}) and 48 cm^{-1} (B_{1g}) for the undoped $\text{LuNi}_2\text{B}_2\text{C}$, which are much less anisotropic than the values in $\text{YNi}_2\text{B}_2\text{C}$ (40 and 49 cm^{-1} , respectively).[1] The anisotropy of the peak positions (and thus the apparent gap values) seems to be lessened as Co-doping increases. The normal state responses (bottom spectra) show curvatures at around $35\text{-}50 \text{ cm}^{-1}$ depending on the amount of Co-doping, which might be responsible for the apparent insensitivity of the 2Δ peak to the Co-doping in the superconducting state.

A comparison of the data for different Co dopings to the theory for Raman scattering in disordered conventional superconductors developed in Ref.[5] is presented in Fig. 1. The theory has been augmented to include electron-phonon and electron-paramagnon inelastic scattering[6]. The relevant fit parameters are the magnitude of gap Δ and the elastic scattering rate $1/\tau_L$ for $L = \text{B}_{1g}, \text{B}_{2g}$ channels. Other parameters entering into the self energies (such as the DOS at the Fermi level, Debye energy, electron-phonon coupling, and the Stoner factor) are taken from Ref. [7]. We used $\Delta = 20 \text{ cm}^{-1}$ for $x = 0$ and 0.015 and used $\Delta = 19 \text{ cm}^{-1}$ for $x = 0.03$. The values

Figure 1. Raman spectra in B_{2g} (top) and B_{1g} (middle) from $\text{Lu}(\text{Ni}_{1-x}\text{Co}_x)_2\text{B}_2\text{C}$ ($x = 0.0, 0.015, 0.03$) at 7 K. The bottom spectra are for B_{2g} in the normal state ($T \approx 17$ K), and similar spectra (not shown) were obtained for B_{1g} . Dotted ($x=0$), dot-dashed ($x=0.015$), and dashed lines ($x=0.03$) are fit to the theory for conventional superconductors. The $x=0$ (0.015) data in B_{1g} (at 7 K) and B_{2g} (at 17 K) have been shifted by 30 (20) and 20 (10) units for clarity.